VIRGINIA DEPARTMENT OF TRANSPORTATION MATERIALS DIVISION REPORT ON THEORETICAL MAXIMUM DENSITY AND OPTIMUM MOISTURE CONTENT (VTM-1)

3/28/2025 9:24 AM	Production Year:	2025
Boxley Materials Company	Plant Name:	Lawyer's Road
3003-2014-01	Max. Dry Density (-No.4 portion):	132.8
Aggregate Base Material-Type I	Optimum Moisture Content (-No.4 portion):	7.2%
21A	Bulk Specific Gravity:	2.720
0.4%	Average percent of +No.4 material:	53.8%
	Number of Samples Referenced:	2
Corrected Maximum Dry Density (lbs/ft³)	150.4	
	Boxley Materials Company 3003-2014-01 Aggregate Base Material-Type I 21A 0.4%	Boxley Materials Company 3003-2014-01 Aggregate Base Material-Type I 21A 0.4% Plant Name: Max. Dry Density (-No.4 portion): Optimum Moisture Content (-No.4 portion): Bulk Specific Gravity: Average percent of +No.4 material: Number of Samples Referenced:

NOTE: This report has been generated by the Materials Information Tracking System (MITS) / Producer Lab Analysis and Information Details (PLAID).

4.1

Corrected Optimum Moisture Content (%)

Form VTM-1 Rev 01/2020 Page 1 of 1