

**VIRGINIA DEPARTMENT OF TRANSPORTATION  
MATERIALS DIVISION  
REPORT ON THEORETICAL MAXIMUM DENSITY AND OPTIMUM MOISTURE CONTENT  
(VTM-1)**

Report Date:	3/21/2023 1:18 PM	Production Year:	2023
Producer Name:	Boxley Materials Company	Plant Name:	Piney River
Job Mix ID:	3034-2014-03	Max. Dry Density (-No.4 portion):	135.4
Type Mix:	Aggregate Base Material-Type I	Optimum Moisture Content (-No.4 portion):	8.2%
Size Aggregate:	21B	Bulk Specific Gravity:	2.740
Absorption::	0.5%	Average percent of +No.4 material:	
		Number of Samples Referenced:	0

Corrected Maximum Dry Density (lbs/ft³)	N/A
Corrected Optimum Moisture Content (%)	N/A

**NOTE:** This report has been generated by the Materials Information Tracking System (MITS) /  
Producer Lab Analysis and Information Details (PLAID).