

**VIRGINIA DEPARTMENT OF TRANSPORTATION
MATERIALS DIVISION
REPORT ON THEORETICAL MAXIMUM DENSITY AND OPTIMUM MOISTURE CONTENT
(VTM-1)**

Report Date:	5/17/2024 2:29 PM	Production Year:	2024
Producer Name:	Boxley Materials Company	Plant Name:	Martinsville Stone Corp.
Job Mix ID:	2009-2014-01	Max. Dry Density (-No.4 portion):	134.1
Type Mix:	Aggregate Base Material-Type I	Optimum Moisture Content (-No.4 portion):	8.0%
Size Aggregate:	21A	Bulk Specific Gravity:	2.810
Absorption::	0.5%	Average percent of +No.4 material:	52.7%
		Number of Samples Referenced:	4

Corrected Maximum Dry Density (lbs/ft³)	153.1
Corrected Optimum Moisture Content (%)	4.6

NOTE: This report has been generated by the Materials Information Tracking System (MITS) /
Producer Lab Analysis and Information Details (PLAID).