

**VIRGINIA DEPARTMENT OF TRANSPORTATION
MATERIALS DIVISION
REPORT ON THEORETICAL MAXIMUM DENSITY AND OPTIMUM MOISTURE CONTENT
(VTM-1)**

| | | | |
|-----------------|--------------------------------|---|---------------------|
| Report Date: | 5/17/2024 2:31 PM | Production Year: | 2024 |
| Producer Name: | Boxley Materials Company | Plant Name: | Lowmoor (Alleghany) |
| Job Mix ID: | 8025-2021-03 | Max. Dry Density (-No.4 portion): | 135.2 |
| Type Mix: | Aggregate Base Material-Type I | Optimum Moisture Content (-No.4 portion): | 8.4% |
| Size Aggregate: | 21B | Bulk Specific Gravity: | 2.740 |
| Absorption:: | 0.3% | Average percent of +No.4 material: | 56.7% |
| | | Number of Samples Referenced: | 4 |

| | |
|---|-------|
| Corrected Maximum Dry Density (lbs/ft³) | 153.4 |
| Corrected Optimum Moisture Content (%) | 4.4 |

NOTE: This report has been generated by the Materials Information Tracking System (MITS) /
Producer Lab Analysis and Information Details (PLAID).